



MOSS-140

Composition	100%PES FR	
Width	140 + 4 cm.	
Weight	488 gr/m ² ±5 %	707 gr/ml. ±5 %
Custom Code	UE: 6005.38.00	USA: 6005.38.00
Seam slippage resistance (mm)	WARP	WEFT
EN ISO 13936/2:2004; Load method (180 n) - Seam slippage (mm)	1,70	2,50
Abrasion resistance (End point)	50.000	
EN ISO 12947-2:1998		
Abrasion resistance (Change of aspect: 3000 cycles)		
EN ISO 12947/4:1998 & EN 14465:2003/A1:2006 (Annex A)	3 - 4	
(Scale from 1 worst to 5 best)		
Pilling resistance		
EN ISO 12945/2:2000; Modified martindale method (2000 and 7000 cycles)	4 - 5	
(Scale from 1 worst to 5 best)		
Assessment of ignitability	BS5852 source 0 / EN1021-1:2006 (Cigarette test)	PASS
	BS5852 source 1 / EN1021-2:2006 (Match test)	PASS
	CAL TB 117	PASS
Lightfastness	6 - 7	
EN ISO 105-B02:1998 & EN ISO 105 B02/A01:2002		
Colour degradation on blue scale (Scale from 1 worst to 8 best)		
Colour fastness to rubbing	DRY	WET
EN ISO 105-X12:2002	5	4 - 5
(Scale from 1 worst to 5 best)		
Dimensional change domestic washing and drying (%)	WARP	WEFT
EN ISO 3759:2008 - EN ISO 6330:2000/A1:2009 - EN ISO 5077:2008	-3,00%	1,50%
Soiling and cleanability	4 - 5	
FORD FLTM BN 112-08:2005 (Scale from 1 worst to 5 best)		
Washing conditions		

NOTES

Slight colour variations may occur from batch to batch.

ENVIRONMENT

- 100% Oekotex certified yarns
- Exclusive use of chemicals and dyes approved by REACH
- Biocide and PFCs free
- Sustainably manufactured under ISO 14001
- Zero waste production
- 100% made in Barcelona
- Packaging with recycled materials

Fire Certificates:

- EN-1021 Part 1&2 (Cigarette & Match test)
- BS 5852 Source 0&1 (Cigarette & Match test)
- BS 7176 Low Hazard
- NF D 60 013

Acoustic certificate;

- EN ISO 354

When confectioning or washing a sofa cover with velcro, attach a protective strip to avoid damage to the fabric.