



Laboratory number test: IN-00680-2017-B-1
IN-00680/2017-B-1
IN-01415-2015
87019

DROM-FR (YARN)

Composition	47%PES 23%PP 17%MA 13%CO	
Width	140 + 4 cm.	
Weight	479 gr/m ² ±5 %	670 gr/ml. ±5 %
Custom Code	UE: 5801.36.00	USA: 5801.36.00.20
Seam slippage resistance (mm)	WARP	WEFT
EN ISO 13936/2:2004; Load method (180 n) - Seam slippage (mm)	3,80	3,90
Abrasion resistance (Fully worn off) EN ISO 12947-2:1998	50000	
Abrasion resistance (Change of aspect: 3000 cycles) EN ISO 12947/4:1998 & EN 14465:2003/A1:2006 (Annex A) (Scale from 1 worst to 5 best)	4 - 5	
Pilling resistance EN ISO 12945/2:2000; Modified martindale method (2000 and 7000 cycles) (Scale from 1 worst to 5 best)	4 - 5	
Assessment of ignitability	BS5852 source 0 / EN1021-1:2006 (Cigarette test)	PASS
	BS5852 source 1 / EN1021-2:2006 (Match test)	PASS
	CAL TB 117	PASS
Lightfastness EN ISO 105-B02:1998 & EN ISO 105 B02/A01:2002 Colour degradation on blue scale (Scale from 1 worst to 8 best)	6 - 7	
Colour fastness to rubbing EN ISO 105-X12:2002 (Scale from 1 worst to 5 best)	DRY	WET
	4 - 5	4 - 5
Colour fastness to domestic and comercial laundering (30°) EN ISO 105-C06:1997/AC:2009 (Scale from 1 worst to 5 best)	4 - 5	
Dimensional change domestic washing and drying (%) EN ISO 3759:2008 - EN ISO 6330:2000/A1-2009 - EN ISO 5077:2008	WARP	WEFT
	-2,00%	-1,50%
Soiling and cleanability FORD FLTM BN 112-08:2005 (Scale from 1 worst to 5 best)	4	
Washing conditions		

NOTES

Recommendation:
Distance overlock and stitch: 12 mm + 0,5 mm minimum
Needle thickness: 110 Nm
Thread: Polyester - Cotton 74 Tex (n°36)
Stitch density: 4.0 stitches+0,1 stitches/cm

ENVIRONMENT

- 100% Oekotex certified yarns
- GRS certified FR yarn
- Exclusive use of chemicals and dyes approved by REACH
- Biocide free
- Sustainably manufactured under ISO 14001
- Zero waste production
- 100% made in Barcelona

When confectioning or washing a sofa cover with velcro, attach a protective strip to avoid damage to the fabric.