



LIBRA-FR (YARN)

Composition	49%PP 21%MA 16%CO 14%PES	
Width	140 + 4 cm.	
Weight	450 gr/m ² ±5 %	630 gr/ml. ±5 %
Statistical number	UE: 5407.83.00	USA: 5407.83.00.90
Seam slippage resistance (mm)	WARP	WEFT
EN ISO 13936/2:2004; Load method (180 n) - Seam slippage (mm)	<u>1,60</u>	<u>1,00</u>
Abrasion resistance (End point)	66000	
EN ISO 12947-2:1998		
Abrasion resistance (Change of aspect: 3000 cycles)	4 - 5	
EN ISO 12947/4:1998 & EN 14465:2003/A1:2006 (Annex A)		
(Scale from 1 worst to 5 best)		
Pilling resistance	4 - 5	
EN ISO 12945/2:2000; Modified martindale method (2000 and 7000 cycles)		
(Scale from 1 worst to 5 best)		
Assessment of ignitability	BS5852 source 0 / EN1021-1:2006 (Cigarette test)	PASS
	BS5852 source 1 / EN1021-2:2006 (Match test)	PASS
	CAL TB 117	PASS
Lightfastness	>6 -	
EN ISO 105-B02:1998 & EN ISO 105 B02/A01:2002		
Colour degradation on blue scale (Scale from 1 worst to 8 best)		
Colour fastness to rubbing	DRY	WET
EN ISO 105-X12:2002	<u>4 - 5</u>	<u>4 - 5</u>
(Scale from 1 worst to 5 best)		
Dimensional change domestic washing and drying (%)	WARP	WEFT
EN ISO 3759:2008 - EN ISO 6330:2000/A1-2009 - EN ISO 5077:2008	<u>-1,00%</u>	<u>-1,00%</u>
Soiling and cleanability	4 - 5	
FORD FLTM BN 112-08:2005 (Scale from 1 worst to 5 best)		
Washing conditions		

ATTENTION: when confectioning or washing the sofa cover with velcro please attach a protective cloth