



VELVETY-FR (YARN)

Composition	86%PES 9%CO 5%MA	
Width	140 + 4 cm.	
Weight	540 gr/m ² ±5 %	756 gr/ml. ±5 %
Statistical number	UE: 5801.36.00	USA: 5801.36.00.20
Seam slippage resistance (mm)	WARP	WEFT
EN ISO 13936/2:2004; Load method (180 n) - Seam slippage (mm)	1,00	1,00
Abrasion resistance (End point)	200000	
EN ISO 12947-2:1998		
Abrasion resistance (Change of aspect: 3000 cycles)	4 - 5	
EN ISO 12947/4:1998 & EN 14465:2003/A1:2006 (Annex A)		
(Scale from 1 worst to 5 best)		
Pilling resistance	5	
EN ISO 12945/2:2000; Modified martindale method (2000 and 7000 cycles)		
(Scale from 1 worst to 5 best)		
Assessment of ignitability	BS5852 source 0 / EN1021-1:2006 (Cigarette test)	PASS
	BS5852 source 1 / EN1021-2:2006 (Match test)	PASS
	CAL TB 117	PASS
Lightfastness	5 - 6	
EN ISO 105-B02:1998 & EN ISO 105 B02/A01:2002		
Colour degradation on blue scale (Scale from 1 worst to 8 best)		
Dimensional change domestic washing and drying (%)	WARP	WEFT
EN ISO 3759:2008 - EN ISO 6330:2000/A1:2009 - EN ISO 5077:2008	-1,60%	-2,00%
Soiling and cleanability	4 - 5	
FORD FLTM BN 112-08:2005 (Scale from 1 worst to 5 best)		
Washing conditions		

NOTES

Iron on reverse side.

ATTENTION: when confectioning or washing the sofa cover with velcro please attach a protective cloth