



Laboratory number test: Document 13686, 13687, 13689, 13690, 13693  
WYS 95101  
2018AN0582

# XEON

Composition	63%WO 18%PP 15%PES 4%CO	
Width	140 + 4 cm.	
Weight	614 gr/m <sup>2</sup> ±5 %	860 gr/ml. ±5 %
Custom Code	UE: 5112.20.00	USA: 5112.20.10.00
Seam slippage resistance (mm)	WARP	WEFT
EN ISO 13936/2:2004; Load method (180 n) - Seam slippage (mm)	2,00	2,00
Abrasion resistance (End point)	40000	
EN ISO 12947-2:1998		
Abrasion resistance (Change of aspect: 3000 cycles)	5	
EN ISO 12947/4:1998 & EN 14465:2003/A1:2006 (Annex A) (Scale from 1 worst to 5 best)		
Pilling resistance	5	
EN ISO 12945/2:2000; Modified martindale method (2000 and 7000 cycles) (Scale from 1 worst to 5 best)		
Assessment of ignitability	BS5852 source 0 / EN1021-1:2006 (Cigarette test)	PASS
	BS5852 source 1 / EN1021-2:2006 (Match test)	PASS
	CAL TB 117	PASS
Lightfastness	5 - 6	
EN ISO 105-B02:1998 & EN ISO 105 B02/A01:2002 Colour degradation on blue scale (Scale from 1 worst to 8 best)		
Colour fastness to rubbing	DRY	WET
EN ISO 105-X12:2002 (Scale from 1 worst to 5 best)	5	5
Dimensional change domestic washing and drying (%)	WARP	WEFT
EN ISO 3759:2008 - EN ISO 6330:2000/A1-2009 - EN ISO 5077:2008	-3,00%	-3,00%
Washing conditions		

## NOTES

Domestic machine wash with special wool program.

Tumble dry on a low cycle.

Dry horizontally.

Iron only on the reverse side using a protective cloth between fabric and iron at minimum iron temperature.

Slight colour variations may occur from batch to batch.

## ENVIRONMENT

- Oekotex certified yarns
- Exclusive use of chemicals and dyes approved by REACH
- Sustainably manufactured under ISO 14001
- Zero waste production
- 100% made in Barcelona

Raport design 27cm x 19cm +/-3,5%

When confectioning or washing a sofa cover with velcro, attach a protective strip to avoid damage to the fabric.