

## Technical Data Sheet

### Q Connect 80g - Sveto

| Parameters       | Standard   | Unit             | Measurement |
|------------------|------------|------------------|-------------|
| Substance        | ISO 536    | g/m <sup>2</sup> | 80 +/- 3    |
| Thickness        | ISO 534    | µm               | 104 +/- 2   |
| Bulk             | ISO 534    |                  | 1,30        |
| Moisture Content | ISO 287    | %                | 4,6 +/- 0,7 |
| Roughness        | ISO 8791   | Bendtsen ml/min  | 250 +/- 50  |
| Whiteness        | ISO 11475  | CIE              | 146 +/- 3   |
| Brightness D65   | ISO 2470-2 | %                | 105 +/- 2   |
| Opacity          | ISO 2471   | %                | 92 +/- 1    |
| Stiffness MD     | ISO 2493   | mN               | 125 +/- 20  |
| Stiffness CD     | ISO 2493   | mN               | 55 +/-10    |

#### Production sites:

The production mills operate in compliance with the following standards



References:  
Product made from ECF Pulp  
ISO 18001 - OHSAS Health & Safety